U.S. DEPARTMENT OF LABOR
Occupational Safety and Health Administration

MATERIAL SAFETY DATA SHEET

Required under USDL Safety and Health Regulations for Ship Repairing, Shipbuilding, and Shipbreaking (29 CFR 1915, 1916, 1917)

▼		SECTI	ONI			
ANUFACTURER'S NAME	EMERGENCY TELEPHON			NO.	•	
Expanded Rubber & Plasti	~ C	orn		(213) 321-426	٥	······································
DOOPES (Number Street City State, and ZIP Co	oae)			•	:	
14000 S. Western Ave. Ga	rder	a, Ca	90249 TRADE	NAME AND SYNONYMS		
HEMICAL NAME AND SYNONYMS Polyester PolyoI				foam		
WEMICAL FAMILY		•	FORMULA	10. Component R		
Polyurethane Polyhydroxyl Com	pound	1	DAC #	DPM 6117		
OFOTION	1 11	UAZAR	DOUS INGRED		•	
SECTION	7 11 -					TLV
PAINTS, PRESERVATIVES, & SOLVENTS	%	TLV (Units)	ALLOYS AND	METALLIC COATINGS	%	(Units
PIGMENTS			BASE METAL		<u> </u>	
CATALYST	<u>. </u>		ALLOYS			
VEHICLE			METALLIC COAT	NGS		
SOLVENTS '			FILLER METAL PLUS COATING O	R CORE FLUX		
ADDITIVES	_		OTHERS .		-	
OTHERS		<u> </u>	<u> </u>			TL'
HAZARDOUS MIXTUR	ES OF	OTHER LI	QUIDS, SOLIDS, OR	GASES	%	(Uni
			,	•		
Polyol Blend		<u></u>			<u> </u>	
Water						
NALEL			•			
		•				
		:				
		:				
SE	CTIO	: I - III N	PHYSICAL DAT	Ά		
SE	стіо	: N III - I	PHYSICAL DAT			0-
BOILING POINT (°F.)	стіо	: N.III - I	SPECIFIC GRAVIT	TY (H ₂ O=1)		.0=
	стіо	: -	SPECIFIC GRAVITOR PERCENT, VOLATED VOLUME (%)	TY (H ₂ O=1) TILE		0-
BOILING POINT (°F.)	стіо	: N -	SPECIFIC GRAVIT	TY (H ₂ O=1) TILE		0=
BOILING POINT (°F.) VAPOR PRESSURE (mm Hg.)	стіо	- III N	SPECIFIC GRAVITOR PERCENT, VOLATED VOLUME (%)	TY (H ₂ O=1) TILE RATE		_0-
BOILING POINT (°F.) VAPOR PRESSURE (mm Hg.) VAPOR DENSITY (AIR=1)	стіо	- III - I	SPECIFIC GRAVITOR PERCENT, VOLATED VOLUME (%)	TY (H ₂ O=1) TILE RATE	1	_0=
BOILING POINT (°F.) VAPOR PRESSURE (mm Hg.) VAPOR DENSITY (AIR=1) SOLUBILITY IN WATER APPEARANCE AND ODOR			SPECIFIC GRAVITED PERCENT, VOLABY VOLUME (%) EVAPORATION F	TY (H ₂ O=1) TILE RATE _ =1)	1	0-
BOILING POINT (°F.) VAPOR PRESSURE (mm Hg.) VAPOR DENSITY (AIR=1) SOLUBILITY IN WATER APPEARANCE AND ODOR			SPECIFIC GRAVITOR PERCENT, VOLATED VOLUME (%)	TY (H2O=1) TILE RATE _ =1) AZARD DATA		
BOILING POINT (°F.) VAPOR PRESSURE (mm Hg.) VAPOR DENSITY (AIR=1) SOLUBILITY IN WATER APPEARANCE AND ODOR SECTION IV	- FI		SPECIFIC GRAVITED PERCENT, VOLABY VOLUME (%) EVAPORATION F	TY (H2O=1) TILE RATE =1) AZARD DATA		
BOILING POINT (°F.) VAPOR PRESSURE (mm Hg.) VAPOR DENSITY (AIR=1) SOLUBILITY IN WATER APPEARANCE AND ODOR SECTION IV FLASH POINT (Method used) 300°F Densky Martin C.C.	- FI	RE AND	SPECIFIC GRAVITATION FOR STANDARD STAND	TY (H2O=1) TILE RATE =1) AZARD DATA	1	
BOILING POINT (°F.) VAPOR PRESSURE (mm Hg.) VAPOR DENSITY (AIR=1) SOLUBILITY IN WATER APPEARANCE AND ODOR SECTION IV FLASH POINT (Method used) 300°F Pensky Martin C.C EXTINGUISHING MEDIA	- FI		SPECIFIC GRAVITATION FOR STANDARD STAND	TY (H2O=1) TILE RATE =1) AZARD DATA	1 1	
VAPOR PRESSURE (mm Hg.) VAPOR DENSITY (AIR=1) SOLUBILITY IN WATER APPEARANCE AND ODOR SECTION IV FLASH POINT (Method used) 300°F Densky Martin C.C EXTINGUISHING MEDIA Water	- FI	RE AND	PERCENT, VOLABY VOLUME (%) EVAPORATION F (TY (H2O=1) TILE RATE =1) AZARD DATA		
BOILING POINT (°F.) VAPOR PRESSURE (mm Hg.) VAPOR DENSITY (AIR=1) SOLUBILITY IN WATER APPEARANCE AND ODOR SECTION IV FLASH POINT (Method used) 300°F Pensky Martin C.C EXTINGUISHING MEDIA	- FI	RE AND	SPECIFIC GRAVITOR PERCENT, VOLABY VOLUME (%) EVAPORATION F EXPLOSION H FLAMMABLE	TY (H2O=1) TILE RATE =1) AZARD DATA		
BOILING POINT (°F.) VAPOR PRESSURE (mm Hg.) VAPOR DENSITY (AIR=1) SOLUBILITY IN WATER APPEARANCE AND ODOR SECTION IV FLASH POINT (Method used) 300°F Densky Martin C.C EXTINGUISHING MEDIA Water SPECIAL FIRE FIGHTING PROCEDURES Self contained breathin	- FI	RE AND	PERCENT, VOLABY VOLUME (%) EVAPORATION F (TY (H2O=1) TILE RATE =1) AZARD DATA		
VAPOR PRESSURE (mm Hg.) VAPOR DENSITY (AIR=1) SOLUBILITY IN WATER APPEARANCE AND ODOR SECTION IV FLASH POINT (Method used) 300°F Densky Martin C.C EXTINGUISHING MEDIA Water	- FI	RE AND	SPECIFIC GRAVITOR PERCENT, VOLABY VOLUME (%) EVAPORATION F EXPLOSION H FLAMMABLE	TY (H2O=1) TILE RATE =1) AZARD DATA		Uel

SECTION V - HEALTH HAZARD DATA								
		STION	V - HEAL	I H HAZARD DA	ATA .			
THRESHOLD LIMIT	value shed							
Not established EFFECTS OF OVEREXPOSURE None observed. This type of polyester may be regarded as physiologically								
INDOCUOUS. EMERGENCY AND FIRST AID PROCEDURES								
Skin; Flush with soap and water								
Eyes: Flush with copious amounts of water								
SECTION VI - REACTIVITY DATA								
				S TO AVOID				
STABILITY	UNSTABLE							
	STABLE .							
INCOMPATABILITY (Materials to avoid)								
HAZARDOUS DECO	MPOSITION PRODUC	TS W						
Aliphetic F	ragments, CO,	-		CONDITIONS TO	CVOID			
HAZARDOUS POLYMERIZATION	WILL NOT O							
	WILL NOT O							
			•					
	· SECT	ION VI	I - SPILL	OR LEAK PROC	EDURES			
STEPS TO BE TAKE			. EASED OR 9	SULED.				
Absorb with	oil absorbing	Compo	ounding a	nd flush with	large volumes of hot water.			
With proper precautions, solvents such as methylene chloride may be used.								
WASTE DISPOSAL METHOD Waste material may be incinerated under conditions which meet federal state and								
local environmental control regulations.								
SECTION VIII - SPECIAL PROTECTION INFORMATION								
1	OTECTION (Specify 1	ype)						
None required VENTILATION LOCAL EXHAUST			SPECIAL					
No special requirements MECHANICAL (Gueral)			OTHER					
				EYE PROTECTIO	N			
Rubber gloves for cleanliness Liquid goggles								
OTHER PHOTECTI	VE EQUIPMENT	· .						
SECTION IX - SPECIAL PRECAUTIONS								
PRECAUTIONS TO BE TAKEN IN HANDLING AND STORING This material is hygroscopic and containers should be tightly closed to prevent								
contamination with foreign material and moisture.								
OTHER PRECAUTIONS Recommended storage temperature is 65°- 85°F								
Recommended storage temperature 15 07 - 07 F								

680 934.110

Form OSHA-20 Rev. May 72